



## Industrial Research Services

Manufacturing & Infrastructure Technology, Graham Road (PO Box 56), Highett, Victoria, Australia 3190  
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: http://www.cmit.csiro.au

Registered Testing Authority - Building Code of Australia

5 June 2006

Our Ref. EN13 / 46 03/0212

### TEST REPORT No. 3568s

Requested by: ATTAR  
on (date): 1 June 2006  
Manufacturer: Unknown  
Product Desc.: Thru-Flow Interlocking Panels  
1200mm x 600mm

Sampling details:  
Where: Delivered  
Date: 1 June 2006  
By whom: Courier  
How (methods): N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results of any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it. The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 3 pages

#### SUMMARY OF SLIP RESISTANCE TESTS PERFORMED:

		Result	Class
AS/NZS 4586:2004	Slip resistance classification of new pedestrian surface materials Appendix C: WET/BAREFOOT Ramp		
	Mean angle of inclination:	29°	C

In order to interpret the classifications, please refer to Standards Australia Handbook 197, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum classifications for a wide variety of locations.

It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.



# Industrial Research Services

Manufacturing & Infrastructure Technology, Graham Road (PO Box 56), Highett, Victoria, Australia 3190  
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: http://www.cmit.csiro.au

REPORT NO: 3568s  
ISSUE DATE: 5 June 2006  
MANUFACTURER: Unknown  
PRODUCT DESC: Thru-Flow Interlocking Panels  
1200mm x 600mm

Page 2 of 3

## SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

### WET/BAREFOOT RAMP TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH  
AS/NZS 4586:2004 (Appendix C)

Test Date: 5 June 2006

Location: Slip Resistance Laboratory

Sample Fixed

Joint width: N/A mm

Surface structure:  Smooth  
 Profiled  
 Structured


### RESULTS

		Actual mean	Reported mean
Mean angle of inclination:	Calibration Board A:	11.01 °	11 °
	Calibration Board B:	17.41 °	17 °
	Calibration Board C:	26.14 °	26 °
Mean angle of inclination of Test Board:		29.31 °	29 °

### CLASSIFICATION:

Quality Group:

**C**



## Industrial Research Services

Manufacturing & Infrastructure Technology, Graham Road (PO Box 56), Highett, Victoria, Australia 3190  
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: [tiles@csiro.au](mailto:tiles@csiro.au) Web: <http://www.cmit.csiro.au>

---

REPORT NO: 3568s  
ISSUE DATE: 5 June 2006  
MANUFACTURER: Unknown  
TILE DESC: Thru-Flow Interlocking Panels  
1200mm x 600mm

---

Page 3 of 3

Date and Place 5 June 2006, Highett, Vic

Name, Title and Signature:

A handwritten signature in black ink, appearing to read "Peter Westgate", is written over the signature line.

**PETER WESTGATE**  
Senior Laboratory Technician

tel: 61 3 92526108  
Fax: 61 3 92526244  
Email: [Peter.Westgate@csiro.au](mailto:Peter.Westgate@csiro.au)

Consulting services are available if further detailed analysis of the test results are required.

---

PR:W050606-10:40:17